

Steelguard 551

Thin Film Intumescent Coating

Product Data/ Application Instructions

- Solvent based thin film intumescent
- 60 minutes fire protection of structural steel
- On-site or off-site application
- Up to 1.5 mm dry film thickness application in a single coat
- For use in C1, C2, C3 & C4 internal & external environments - no sealer coat required for dry internal C1 service conditions (ISO 12944)

Typical Uses

Intumescent fire protection for internal and external structural steel. Suitable for I section columns, beams and hollow sections. Intended for on-site application using manual airless spray equipment. Can also be applied by brush. Also suitable for off-site application either by manual airless spray or via automatic applications with pre-heat and accelerated drying facilities. Steelguard 551 is weather resistant for up to 12 months in normal conditions thereby facilitating the transport, storage and erection phases on construction projects. During these periods running/pooling water, hot humid environments and immersed conditions must be avoided.

Approvals

Steelguard 551 has been tested to National and International standards for cellulosic fire exposure (ISO 834) and subsequently assessed and certified in accordance with various National requirements. Please contact your PPG Protective and Marine Coatings representative for latest information relating to local market requirements and approvals. For given projects PPG Protective and Marine Coatings can provide customers with loading data and material consumption calculations stipulated by required fire protection, steel section designation and local requirements. Standard loading tables can be made available where applicable.



**APPROVED PRODUCT
CF 551**

Physical Data

Appearance when dry	matt	
Colour	white, grey	
Components	1	
Volume solids *.....	75 ± 3%	
VOC**		
EC SED 1999/13/EC	257 g/kg (346g/l)	
UK PG6/23 (92) Appendix 3...	330 g/l	
Curing mechanism	solvent release	
Loading requirements.....	In order to establish the dry film thickness required to give the specified fire resistance reference should be made to the products A/V m ⁻¹ (Hp/A) loading or limiting temperature tables	
Dry film thickness (microns) ..	200 400 500 700 1000	
Wet film thickness (microns) .	270 535 665 935 1335	
Theoretical coverage (m ² /l)	3.75 1.88 1.50 1.07 0.75	
Specific gravity	1.35 kg/l	
Flashpoint (closed cup)		
Steelguard 551	25°C	77°F
Amercoat 65	24°C	75°F
Potlife	not applicable	
Thinner	not normally necessary	
Cleaner	Amercoat 65	

*Volume Solids is measured in accordance with ASTM D2697 modified. Slight variations of up to ±3% may occur due to testing variances.

** VOC figures are quoted according to the EC directive 1999/13/EC which are theoretically calculated figures and the UK PG6/23 (92) Appendix 3 which are practically determined figures.

Steelguard 551

Surface Preparation

Applied over a blasted and suitably primed steel substrate. The surface must be dry and free of dust, salts, grease and other contaminants immediately before coating. The primer used should be applied in accordance with the specific technical data sheet instructions, and must be approved by PPG to ensure compatibility with the Steelguard 551. Suitable PPG primers include Amercoat 71, 139, 182ZPHB, 3146P, 4116, Steelguard 3290, and Amercoat 68 series. The total dry film thickness of primer coats should generally not exceed 150 microns. For epoxy primers the maximum allowable dry film thickness may be extended, consult your PPG representative prior to intumescent application.

For off-site application Steelguard 551 may be applied directly to the blast cleaned substrate provided the steelwork is to be used in dry internal C1 conditions and the dry film thickness exceeds 400 microns. The steel should be abrasive blast cleaned to ISO 8501-1 Sa 2½ with a blast profile of approximately 50-75 microns and should not exceed 100 microns. Coating should occur before degradation of the surface takes place. If oxidation occurs then the steel should be re-prepared. The surface must be dry and free of dust, salts, grease and other contaminants immediately before coating.

Mixing

Stir thoroughly before use until the product is uniform throughout. This may cause an apparent thinning effect which is normal for this product. A power mixer should be used.

Application Methods

AIRLESS SPRAY - Use a pump capable of producing a minimum pressure at the tip of 2800 psi (200 kg/cm²). A 30 mesh/500 micron internal filter is recommended. Tip size 19-25 thou' (0.48-0.63mm). For on-site application Steelguard 551 can be applied in a single coat up to 1.5mm dft. For off-site application it is recommended that the product is applied in 700 microns dry film thickness coats allowing a minimum of 8 hours drying at 15°C (59°F) between each coat.

BRUSH – Apply evenly using a clean, well-loaded brush at up to 300 microns dry film thickness per coat. As a guide allow at least 2 hours drying at 20°C (68°F) between coats.

Drying Characteristics

Drying times will vary considerably depending on ambient conditions, A/V m⁻¹ (Hp/A) of section being coated and applied film thickness. As a guide, at 15°C (59°F) a 700 microns dry film thickness coating will be touch dry in 1 hour and hard dry after approximately 40 hours. For further details on the drying times of Steelguard 551 refer to the product drying tables or contact your PPG representative.

Overcoating

The standard recommended topcoat for Steelguard 551 is Steelguard 2458 which allows for fast overcoating and job completion. Other approved topcoats but with longer overcoating periods include Amercoat 450 series, Amercoat 4310, Amercoat 2136 and PSX 700#. No sealer is required for internal C1 service conditions unless for cosmetic reasons. For internal C2 service conditions Steelguard 551 must be adequately sealed with Steelguard 2458 at 60 microns dry film thickness or other approved topcoat. For C3 & C4 external service conditions Steelguard 551 must be adequately sealed with two coats Steelguard 2458 at 120 microns total dry film thickness or other approved topcoat. Please contact your PPG representative for specific recommendations. It is important that the specified intumescent thickness has been achieved before any topcoating.
(# Amercoat 71TC required as a tie coat)

Application Data

Substrate primed abrasive blasted steel

Application methods airless spray, brush

Environmental Conditions

Relative humidity:	up to 85%	
Surface temperature:	5 – 50°C	41 – 122°F
Air temperature	5 – 50°C	41 – 122°F

Surface temperature must be at least 3°C (5°F) above the dew point to prevent moisture condensation on the surface.

Thinner not normally necessary
Amercoat 65 can be used when needed (up to 5% by volume),
However wet/ dry film measurement result will differ & lower max film build as result will have to be considered

Cleaner Amercoat 65

Steelguard 551

Providing the steel is suitably primed and the dry film thickness of the intumescent coating exceeds 250 microns, Steelguard 551 can be left externally without a topcoat for up to 12 months. During this period, however, Steelguard 551 must be protected from pooling and running water, hot humid environments and immersed conditions.

Steelguard 551 must have sufficient drying time before exposure in external conditions. As a guide, at 15°C (59°F), for a dry film thickness of 700 microns, a minimum drying period of 40 hours is recommended from time of application of the final coat before exposure.

Refer to product drying tables for drying and overcoating schedules.

Shipping Data

Pack size	20 and 200 litres
Shipping weight	approx. 29 kg (20 l.)
Shelf life	1 year from shipment date when stored indoors in unopened, original containers at 5 to 40°C (41 to 104°F).

Application Procedure:

1. Flush equipment with recommended cleaner before use.
2. Stir to an even consistency with a power mixer.
3. Thinning is normally not required for airless spray.
4. For airless spray apply a wet even coat in parallel passes. Overlap each pass 50% to avoid bare areas, pinholes or holidays.
5. Give special attention to welds, rough spots, sharp edges and corners, rivets, bolts, etc.
6. Application at 540 microns wet film thickness will normally provide 400 microns dry film.
7. Check thickness of dry coating with a non-destructive dry film thickness gauge, such as Mikrotest or Elcometer. If less than specified thickness, apply additional material as needed.
8. Limited areas of damage should be repaired using Steelguard 2451 intumescent repair compound to the specified dry film thickness. Repair larger areas either by spray or brush using Steelguard 551.
9. For repair of damaged primerless systems where bare steel is exposed, a suitable primer should be applied prior to re-application of the intumescent coating.
10. In confined areas ventilate with clean air during application and drying until all solvents are removed. Temperature and humidity of ventilating air must be such that moisture condensation will not form on surface.
11. Clean all equipment with recommended cleaner immediately after use or at least at the end of each working day or shift.

Before using the product, read the label on the can and consult the material safety data sheet.

Steelguard 551

Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

Warranty

PPG warrants its products to be free from defects in material and workmanship. PPG's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at PPG's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

PPG makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall PPG be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by PPG, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

Limitation of Liability

PPG's liability on any claim of any kind, including claims based upon PPG's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim. In no event shall PPG be liable for consequential or incidental damages.

Due to PPG's policy of continuous product improvement, the information contained in this Product Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product Data/Application Instructions always refer to the PPG Protective & Marine Coatings website at www.ppgpmc.com

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.

